

**TECHNICAL DATA SHEET****DESCRIPTION**

PUMA<sup>®</sup> 2130 is a mixture of 33% triethylenediamine and 67% dipropyleneglycol. It is completely soluble in water and is miscible with polyols, fluorocarbons and stannous catalysts.

**APPLICATION**

PUMA<sup>®</sup> 2130 is a low viscosity, easy handling gelation catalyst, used in the manufacture of all types of polyurethane foams.

**GUARANTEED VALUES**

Parameter	Value
triethylenediamine content	33% min.
Water content	0.3% max.

**TYPICAL VALUES**

Parameter	Value
Physical State	Clear liquid
Odor	Ammoniacal
pH	10.20
Flash Point (TCC)	>110 °C / 230 °F
Specific Gravity (Water = 1)	1.03
Vapor Pressure at 21 °C (70 °F)	2.00 mmHg
Boiling Point	>149 °C / >300 °F
Solubility in Water	100%
Drum net weight	200kg / 441lb

**NOTES**

The information contained herein is, to the best of our knowledge and belief, accurate. We make no guarantee of results and assume no liability for damages incurred by following these suggestions or any other product use. Nothing contained herein is to be construed as a recommendation for use in violation of any patents or of applicable laws or regulations.